

# Amodel® DW-1150

## polyphthalamide

Amodel® DW-1150 is a 50% glass-fiber-reinforced resin designed for high strength and stiffness and improved hydrolytic stability. This material has low moisture absorption and a low coefficient of thermal expansion, which means excellent dimensional stability. Creep resistance is also exceptional.

This grade has been approved for use with potable water in the United States, France, Germany, and the United Kingdom.

- Black: DW-1150 BK938

### General

|                        |   |   |
|------------------------|---|---|
| Material Status        | • Commercial: Active  |   |
| Availability           | <ul style="list-style-type: none"> <li>• Africa &amp; Middle East</li> <li>• Asia Pacific</li> <li>• Europe</li> </ul>  | <ul style="list-style-type: none"> <li>• Latin America</li> <li>• North America</li> </ul>  |
| Filler / Reinforcement | • Glass Fiber, 50% Filler by Weight   |   |
| Features               | <ul style="list-style-type: none"> <li>• Chemical Resistant</li> <li>• Chlorine Resistant</li> <li>• Creep Resistant</li> <li>• Good Dimensional Stability</li> </ul> | <ul style="list-style-type: none"> <li>• High Stiffness</li> <li>• High Strength</li> <li>• High Temperature Strength</li> <li>• Low Moisture Absorption</li> </ul> |
| Uses                   | <ul style="list-style-type: none"> <li>• Appliances</li> <li>• Consumer Applications</li> <li>• Filters</li> <li>• Housings</li> </ul>                                | <ul style="list-style-type: none"> <li>• Industrial Applications</li> <li>• Plumbing Parts</li> <li>• Pump Parts</li> <li>• Valves/Valve Parts</li> </ul>           |
| RoHS Compliance        | • RoHS Compliant  |   |
| Appearance             | • Black   | • Natural Color   |
| Forms                  | • Pellets   |   |
| Processing Method      | • Injection Molding   |   |

| Physical | Typical Value | Unit  | Test method |
|----------|---------------|-------|-------------|
| Density  | 1.68          | g/cm³ | ISO 1183/A  |

| Mechanical                      | Typical Value | Unit | Test method |
|---------------------------------|---------------|------|-------------|
| Tensile Modulus                 | 18000         | MPa  | ISO 527-2   |
| Tensile Stress (Break, 23°C)    | 260           | MPa  | ISO 527-2   |
| Tensile Strain (Break, 23°C)    | 1.9           | %    | ISO 527-2   |
| Flexural Modulus (23°C)         | 18500         | MPa  | ISO 178     |
| Flexural Strain at Break (23°C) | 2.3           | %    | ISO 178     |
| Flexural Strength (Break, 23°C) | 400           | MPa  | ISO 178     |

| Impact                           | Typical Value | Unit  | Test method |
|----------------------------------|---------------|-------|-------------|
| Charpy Notched Impact Strength   | 12            | kJ/m² | ISO 179     |
| Charpy Unnotched Impact Strength | 80            | kJ/m² | ISO 179     |
| Notched Izod Impact Strength     | 12            | kJ/m² | ISO 180     |

| Thermal  | Typical Value | Unit | Test method |
|--|---------------|------|-------------|
| Heat Deflection Temperature<br>1.8 MPa, Unannealed | 300           | °C   | ISO 75-2/Af |

# Amodel® DW-1150

## polyphthalamide

| Injection              | Typical Value  | Unit |
|------------------------|----------------|------|
| Drying Temperature     | 120            | °C   |
| Drying Time            | 4.0            | hr   |
| Suggested Max Moisture | 0.030 to 0.060 | %    |
| Rear Temperature       | 315 to 330     | °C   |
| Middle Temperature     | 320 to 340     | °C   |
| Front Temperature      | 325 to 345     | °C   |
| Processing (Melt) Temp | 340 to 360     | °C   |
| Mold Temperature       | 150            | °C   |

### Injection Notes

Mold Temperature:

- Higher tool temperatures might be required for thin wall sections

Storage:

- Amodel® compounds are shipped in moisture-resistant packages at moisture levels according to specifications. Sealed, undamaged bags should be preferably stored in a dry room at a maximum temperature of 50°C (122°F) and should be protected from possible damage. If only a portion of a package is used, the remaining material should be transferred into a sealable container. It is recommended that Amodel® resins be dried prior to molding following the recommendations found in this datasheet and/or in the Amodel® processing guide.

### Notes

Typical properties: these are not to be construed as specifications.

**www.solvay.com**

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa

SpecialtyPolymers.Americas@solvay.com | Americas

SpecialtyPolymers.Asia@solvay.com | Asia and Australia

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2020 Solvay Specialty Polymers. All rights reserved.

